

Nr.	EN/DIN	AISI	UNS	Nr.	EN/DIN	AISI	UNS
Ferritic, martensitic & precipitation hardening Stainless Steel				Austenitic Stainless Steel			
1.4000	X 6 Cr 13	410 S	S 41008	1.4301	X 5 Cr Ni 18-10	304	S 30400
1.4006	X 12 Cr 13	410	S 41000	1.4303	X 4 Cr Ni 18-12	305	S 30500
1.4016	X 6 Cr 17	430	S 43000	1.4305	X 8 Cr Ni S 18-9	303	S 30300
1.4021	X 20 Cr 13	420	S 42000	1.4306	X 2 Cr Ni 19-11	304 L	S 30403
1.4034	X 46 Cr 13			1.4307	X 2 Cr Ni 18-9	304 L	S 30403
1.4057	X 17 Cr Ni 16-2	431	S 43100	1.4310	X 10 Cr Ni 18-8	301	S 30100
1.4104	X 14 Cr Mo S 17	430 F	S 43020	1.4541	X 6 Cr Ni Ti 18-10	321	S 32100
1.4112	X 90 Cr Mo V 18	440 B	S 44003	1.4550	X 6 Cr Ni Nb 18-10	347	S 34700
1.4122	X 39 Cr Mo 17-1			1.4401	X 5 Cr Ni Mo 17-12-2	316	S 31600
1.4313	X 3 Cr Ni Mo 13-4		S 41500	1.4404	X 2 Cr Ni Mo 17-12-2	316 L	S 31603
1.4418	X 4 Cr Ni Mo 16-5-1			1.4429	X 2 Cr Ni Mo N 17-13-3	316 LN (Mo+)	S 31653
1.4512	X 2 Cr Ti 12	409	S 40900	1.4435	X 2 Cr Ni Mo 18-14-3	316 L (Mo+)	S 31603
1.4542	X 5 Cr Ni Cu Nb 16-4	630	S 17400	1.4436	X 3 Cr Ni Mo 17-13-3	316 (Mo+)	S 31600
1.4568	X 7 Cr Ni Al 17-7	631	S 17700	1.4439	X 2 Cr Ni Mo N 17-13-5	317 LN	S 31753
1.4594	X 5 Cr Ni Mo Cu Nb 14-5	XM-12	S 15500	1.4571	X 6 Cr Ni Mo Ti 17-12-2	316 Ti	S 31635
Duplex & Superduplex				High-Temperature resisting Stainless Steel			
1.4362	X 2 Cr Ni N 23-4		S 32304	1.4948	X 6 Cr Ni 18-11	304 H	S 30409
1.4410	X 2 Cr Ni Mo N 25-7-4	A182 F53	S 32750	1.4550	X 6 Cr Ni Nb 18-10	347 H	S 34709
1.4460	X 3 Cr Ni Mo N 27-5-2	329	S 32900	1.4876	X 10 Ni Cr Al Ti 32-20		N 08800
1.4462	X 2 Cr Ni Mo N 22-5-3	A182 F51	S 31803	1.4713	X 10 Cr Al 7		
1.4462	X 2 Cr Ni Mo N 22-5-3	A182 F60	S 32205	1.4724	X 10 Cr Al 13		
Superaustenitic Stainless Steel				1.4742	X 10 Cr Al 18		
1.4465	X 1 Cr Ni Mo N 25-25-2		N 08310	1.4749	X 18 Cr N 28	446	S 44600
1.4466	X 1 Cr Ni Mo N 25-22-2	310 MoLN	S 31050	1.4762	X 10 Cr Al 24		
1.4529	X 1 Ni Cr Mo Cu N 25-20-7		N 08926	1.4828	X 15 Cr Ni Si 20-12		
1.4537	X 1 Cr Ni Mo Cu N 25-25-5		N 08932	1.4833	X 7 Cr Ni 23-14	309 S	S 30908
1.4539	X 1 Ni Cr Mo Cu 25-20-5	904 L	N 08904	1.4835	X 10 Cr Ni Si N 21-11		S 30815
1.4547	X 1 Cr Ni Mo Cu N 20-18-7	F44	S 31254	1.4841	X 15 Cr Ni Si 25-20	314	S 31400
1.4563	X 1 Ni Cr Mo Cu 31-27-4		N 08028	1.4845	X 12 Cr Ni 25-21	310 S	S 31008
1.4565	X3CrNiMnMoNbN 23-17-5-3		S 34565	1.4864	X 12 Ni Cr Si 36-16	330	N 08330



Kontakt

Damstahl ab
 dsm.sales@damstahl.com
 +46 40 59 69 00
 www.damstahl.se