

Tabell - Korrosionsklasser

Stålsort F:Ferrit A:Austenit FA:Ferrit-Austenit	EN-beteckning	ASTM-beteckning	PREN-tal	Korrosionsklass
F	1.4003	S41050	11,5	
A	1.4301	304	18,1	
A	1.4401	318	24,13	
A	1.4404	316L	24,13	C3-C4
A	1.4571	316Ti	23,73	C3-C4
A	1.4436	316	25,48	C3-C4 (E201)
A	1.4439	S31726	31,16	C3-C4
FA (Duplex)	1.4462	S32205	34,95	C5/M(E201)
A	1.4539	N08904	41,0	C5/M
FA (Duplex)	1.4410	S32750	43,0	C5/M
A	1.4565	S34565	53,35	C5/M
A	1.4547	S31254	49,4	C5/M
A	1.4529		49,1	C5/M